



# Lite Bond

Code M55M1--

## PRODUCT FEATURES

This product is based on high elongation polyester resin, without glass fibre. It is distinguished by its low specific weight (lower than 1). It is ideally applied where a high adhesion between the elements and a low weight are required.

## VERSIONS

Only one.

## APPLICATION

It requires 1% to 2% MEKP catalyst to harden. Spatula use. Drip-free, even in case of high thickness. It contains a colour change indicator additive that allows checking the uniformity in the dispersion of the hardener.

## PACKAGE

15 Kg

## PROPERTIES OF THE NON-CURED PRODUCT

PROPERTY	METHOD	UNIT OF MEASUREMENT	VALUE
Appearance	/	/	Very viscous and thixotropic fluid
Viscosity at 25°C	istr. 3 I.T.I.P.	cps	60.000 – 100.000
Mass Gel time at 25°C <sup>1</sup>	istr. 2 I.T.I.P.	minutes	10 – 20
Stability	istr. 7 I.T.I.P.	months	max 4
Interlaminar shear strength test	ASTM D 2733	Kg/cm <sup>2</sup>	23

Remarks

<sup>1</sup> Catalysis 2% MEKP 50% mass 100 g

## IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us of the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.