

LOCTITE EDAG 461SS E&C

August 2014

PRODUCT DESCRIPTION

LOCTITE EDAG 461SS E&C provides the following product characteristics:

Technology	Polyester Resin
Appearance	Silver
Filler Type	Silver
Solvent	Butyl cellosolve acetate
Cure	Heat cure
Operating Temperature-Maximum	149°C
Product Benefits	<ul style="list-style-type: none"> • Conductive • Screen printable • Extremely flexible • Low electrical resistance • Dries at low temperatures • Good adhesion
Application	Conductive Ink
Typical Assembly Applications	ITO coated film, Membrane switches, Digitizers, Flexible circuits and Electroluminescent lamps
Key Substrates	Polyester and ITO film

LOCTITE EDAG 461SS E&C conductive ink is designed for display applications on ITO film. It consists of very finely divided silver particles dispersed in a thermoplastic resin.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content by Weight, %	75
Viscosity, Brookfield - RVT, mPa·s (cP):	
Spindle 6, speed 20 rpm,	17,000
Density, kg/l	2.34
Shelf Life @ 5 to 27°C (from date of manufacture), year	1
Flash Point ASTM D93-71, Pensky-Martens	74
Closed Cup Flash Tester°C	

TYPICAL SCREEN PRINTING PROCESS

Recommended Thickness

Dry Film, µm	10.0 to 12.5
--------------	--------------

Emulsion Thickness

Solvent resistant emulsion, µm	20 to 37.5
--------------------------------	------------

Recommended Screen Type

Monofilament polyester screen, mesh	157 to 280
Stainless steel screen, mesh	165 to 250

Recommended Squeegee

Polyurethane or other solvent resistant material

Polyester screen, durometer	60
Stainless steel screen, durometer	70

TYPICAL CURING PERFORMANCE

Cure Schedule

- 30 minutes @ 71°C or
- 15 minutes @ 93°C or
- 5 minutes @ 121°C

Percent Volatiles

VOC, g/l	576
----------	-----

Depending on the amount of air flow, curing may be faster.

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties :

Pencil hardness	3B
-----------------	----

Coverage @ 25µm thickness, m ² /kg	6.1
---	-----

Electrical Properties:

Sheet Resistivity @ 25µm, ohms/sq	<0.02
-----------------------------------	-------

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. Do not expose wet ink to direct sunlight.
2. Do not freeze.
3. Keep product container tightly closed when not in use.
4. LOCTITE EDAG 461SS E&C should be thoroughly stirred prior to use. Avoid rapid stirring as this causes air entrapment..
5. LOCTITE EDAG 461SS E&C is supplied ready for use. Should thinning become necessary, dilute 5% by weight with butyl carbitol acetate..
6. If product dries too quickly in the screens, dilute the neat product 5% with butyl carbitol acetate to prolong drying time.

Clean-up

To clean screen and equipment, use Methyleneethylketone (MEK), MIBK, Acetone or similar solvents

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Store in a cool, well ventilated area.

Optimal Storage : 5 to 27 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} = \text{N/mm}^2$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2