

# PLX 200 ECO

## PRODUCT DESCRIPTION

PRE-POLYMER DIAZO photoemulsion suitable for the preparation of screens for textile continuous printing


## APPLICATION FIELDS

Photoemulsion indicated for printing with:  
water based inks

## CHARACTERISTIC

- Colour: blue
- Solid content: 41%
- Viscosity: around 8.500 cps (25°C)
- Excellent edge definition
- Good resolution
- Good exposure latitude
- Suggested screen: from 34 Th/cm a 90 Th/cm
- Solvent free

## APPLICATION PROCESS



### FABRIC PREPARATION


New fabric: degrease with products of the Cleanser.

Recovered fabrics: operate in advance with Polistrip series product and then with Cleanser product series.




### SENSIBILIZATION

Add Diazo micro-HD powder directly into the emulsion, without dissolving the diazo in demineralized water. Let stand for a few hours to allow the necessary disaeration.



### APPLICATION

The application depends on the mesh of the screen. The recommended range is from 34Th/cm to 90 Th/cm. It's recommended to apply a photoemulsion layer on the printing side and a photoemulsion layer on the squeegee side (by following the indicated sequence).



### DRYING

After application, dry the frames horizontally with the printing side down in a ventilated oven for about 60 minutes. It is recommended to dry at a temperature between 30°C and 40°C. Too high temperatures could compromise the development of the frame. Drying times change depending on the amount of applied photoemulsion.

## EXPOSURE

The exposure time is influenced by:

- Type and quality of light source
- From the thickness of the photoemulsion (EOM)

We recommend the use of a metal-halogen lamp UV 5000 W.

For example:


Fabric = 62 Th/cm

Lamp = metal-halogen UV 5000 W

Distance = 140 cm

Exposure time = 90 seconds

Exposure testing is recommended to find the correct time.




## DEVELOPMENT

After the exposure, wet the screen internally and externally, leave the painting dry for a few moments and then rinse with a water jet on the printing side until the details of the drawing are completely opened. If possible, it is recommended to immerse the framework in water at room temperature for about five minutes before development.




## RETOUCHES

Retouches can be made by the sensitized product. Repeat the exposure to the light



## RECOVERY

Screens can be re-used only before any hardening with Polistrip product series




## HARDENING

PLX 200 ECO has to be hardened by means of cold chemical hardening treatment with *Catalyst 210 (cod. M160210K001000)* (see technical data sheet) The emulsion becomes then permanent

Once hardened, the screen can be used:

- After 12 hours if dried at room temperature
- After 45 minutes if dried at 50°C



### SPECIAL RECOMMENDATIONS

Always test the characteristics of the product before starting a production.

Always use the product in a yellow light protected environment.

Sensitized emulsion when stored at a temperature between 4 °C - 10 ° has a pot life of about 4-6 weeks.

The emulsion stored at a maximum temperature of 25 °C has a shelf life of one year.

Safety data sheet available on request

### PACKAGING

M161054EK005000	5 Kg
-----------------	------

### IMPORTANT INFORMATION NOTE

The information contained in this data sheet is not to be considered exhaustive, but anyone who uses the product for any purpose other than that specifically recommended on this document without a precise written confirmation from us, He does it at his own risk.

Although we strive to ensure that all the advice given here about the product is correct, we do not have any control over the quality and conditions of the support, or the multiple factors that may affect the use and application of the product.

Therefore, except for specific written agreements, we do not accept any responsibility - of quality nature and in whatever way it occurs - for the performance of the product, nor for any loss or damage resulting from the unauthorized use of the product.

The information contained in this document is subject to periodic reviews, based on experience and our policy of constant product improvement.