

# Posterfast

Code A31163000

## PRODUCT DESCRIPTION

Removable solvent based ink with high opacity.

## APPLICATION FIELDS

Screen printing ink for printing of removable masking onto paper and paperboard, which are treated through UV varnishes.

This product is dedicated to the printing of lottery tickets, scratch & win tickets, competitions or "scratch & see" effects.

## APPLICATION PROCESS

<b>Substrates</b>	Paper, UV varnished paperboards
<b>Th/Cm</b>	From 43 to 90 Th/Cm
<b>Emulsion</b>	<ul style="list-style-type: none"> <li>• <i>Zero - In SV Plus Viola</i></li> <li>• <i>Zero - In SR-V</i></li> </ul>
<b>Squeegee</b>	Square edge Squeegee hardness 70 - 75 Shores
<b>Drying</b>	Tack-free is reached at room temperature within 20 min., or at 50-60°C for a few minutes
<b>Thinner</b>	<i>Diluyente 90.917 Normale Inodore</i> <i>Diluyente 90.918 Lento</i>
<b>Retarder</b>	<i>90.923 Ritardante Inodore</i> (code A31890923001)
<b>Cleaning</b>	<i>Solvente Lavaggio LQ 90.920</i>
<b>Storage</b>	If kept in its original sealed package, the product has a shelf-life of 2 years
<b>Package</b>	See the product range table
<b>Safety Data Sheet</b>	Available on request

## GENERAL FEATURES

- Matt finishing
- Excellent opacity
- High drying speed
- Very easy to remove
- Excellent stability in the screen

## PREPARATION

Before using it, the ink must be mixed well and, in case, diluted, according to printing requirements.

## TECHNICAL FEATURES

The performance of the product, printed with a 77 th/cm screen, is 30-35 m<sup>2</sup>/Kg. These data are merely an indication, since they depend on the dilution, the substrate and the printing equipment. The best results are achieved by printing onto UV varnished substrates. Concerning this, the use of *Vernice UV 34.890 NF Non Ingiallente Toys* (code A31134890NF005) is recommended.



## SPECIAL INSTRUCTIONS

- Always test the characteristics of the product, before starting production.
- The above information is the result of previous knowledge and experience; it is neither a guarantee nor an assurance.
- It is recommended not to exceed 65-70°C during drying into oven, in order to not compromise the removability of the ink.
- *Posterfast Rub. Rem. Silver NF 63013NF* is recommended for big productions, that means high stacks

## PRODUCT RANGE

CODE	PRODUCT	PACKAGE
A3116303000-	RUB. REM. GOLD	1 and 5 kg
A31163013NF00-	POSTERFAST RUB. REM. SILVER NF	1 and 5 kg

## IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us of the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.