

SERIPLASTIK ADDITIVES

1

DESCRIPTION

All hereunder additives are consistent with all products of the series **SERIPLASTIK**

2

PRODUCTS

CODE		FEATURES	USE
NAME		FLUIDIFICANTE SPECIALE X 241	% ADDITION: [2% - 4%] An excess of fluidifying agent prevents the ink from completely curing and compromises washing fastnesses.
DESCRIPTION	09.899	Plastifying based product. It is used to fluidify the ink and make it more printable.	
NAME		FLUIDIFICANTE WF PHATHALATES FREE	% ADDITION: [2% - 4%] An excess of fluidifying agent prevents the ink from completely curing and compromises washing fastnesses.
DESCRIPTION	58.995	Plastifying agent. It is used to fluidify the ink and make it more elastic after curing.	
NAME		CATALIZZATORE SERIPLASTIK	% ADDITION To COLOURS: [5% - 15%]
DESCRIPTION	12.888	Catalyst for plastisol inks. It may be used to increase the adhesion on such substrates, that are difficult to print. It is able to increase the washing fastnesses and reduce curing temperatures of plastisol inks. Once hardened, the product has a pot-life of 4-6 hours.	
NAME		ADDITIVO X-118	% ADDITION To COLOURS: [5% - 15%] Depending on the desired effect.
DESCRIPTION	09.052	Additive for 3D effects. It may be mixed into colours, to obtain 3D coloured effects with very intense colours.	
NAME		SERIPLASTIK BASE ELASTICIZZANTE	% ADDITION To COLOURS: [5% - 20%] Depending on the desired effect and the fabric to be printed.
DESCRIPTION	12.885	Plastisol neutral base for printing on elastic substrates, such as lycra and stretch cotton. It gives more flexibility and elasticity to plastisol inks.	
NAME		DILUENTE SERIPLASTIK	% ADDITION To COLOURS: [1% - 2%]
DESCRIPTION	99.101	Solvent based product for diluting all the inks of the series SERIPLASTIK .	

3

APPLICATION

Refer to the Technical Data Sheets of the corresponding series (**SERIPLASTIK**).

4

STORAGE

It is recommended to keep the products at a temperature between 18°C and 30°C, away from sunlight.

IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk. While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.