

NXG Series

PRODUCT INFORMATION

The NXG Ink Series has been specifically formulated to adhere to a wide range of print treated substrates while still offering flexibility, water resistance and good light-fastness properties.

The advanced formula of the NXG series has been engineered to withstand changes in viscosity on all multi-color in-line press machinery.

APPLICATION FIELD

End uses include indoor and aoutdoor point of purchase displays, decals, banners and transit signal.

APPLICATION PROCESS

Substrates	Treated Polyethylene Banner Materials, Treated Coroplast™ / Fluted Polyolefin, High Density Polyethylene (HDPE), Reinforced Vinyl Banner Materials, Coated Paper and Board Stocks, Pressure Sensitive Vinyl, Polystyrene, (Styrene), Static Cling Vinyl, Polycarbonate, Card Stock
Th/cm	From 355 to 420 (140 to 165 cm), monofilament polyester is recommended.
Emulsion	Direct emulsions and capillary films which are both solvent resistant, UV compatible and yield a thin deposit of 3 to 7 microns of emulsion over mesh (EOM).
Squeegee	Sharp 70 to 85 single or multi- durometer polyurethane blade
Ink Yield and Coverage	Colors should achieve a yield of 3100 to 3,950 square feet per gallon (73 to 93 square meters per liter) depending upon ink deposit. To ensure optimum ink flexibility, ink economy and UV curing performance a thin ink deposit of .40 to .80 mil (10 to 20 microns) is highly recommended.

Drying	The NXG Ink Series is formulated to cure when exposed to a focused medium pressure mercury vapor UV lamp in a spectral range of 250 and 360 nanometers to initiate cure. NXG will normally cure sufficiently in a single UV lamp unit set at 200 watts per inch (80 watts per cm) at a belt speed of 50 to 75 feet (15 to 22 meters) per minute. Wash up on press with a UV ink
Cleaning	press wash and reclaim with degradents specifically developed for UV inks.
Storage	Store at room temperature, below 100° F (38° C). Always avoid open flames and excessive heat exposure. Protect from freezing.
Packaging	Available in gallon and five-gallon pails. 50 gallon drums can be ordered.
SDS	Available upon request

GENERAL FEATURES

- Advanced Color Gamut[™] Four-Color Process Colors
- Fast Cure Speeds at Low UV Light Dosages
- An Extremely Diverse Adhesion Range
- Good Durability and Water Resistance
- Low Pile Height Rheology
- Up to 2 Year Light-Fastness*
- Automotive Grade Pigments

ADDITIVES AND THINNERS

Stir the ink well before every use. The NXG Ink Series is supplied in a press ready condition for most applications and printing equipment. When the ink is cold or the viscosity of the ink is thicker than desired, it is best to mix the ink thoroughly with a high speed mixer until the ink returns to the proper room temperature and viscosity. If reduction is of the ink viscosity is required, 3901



thinner may be used sparingly by no more than 2 to 5% by weight.

3104 Flattening Paste can be used to change the gloss level of the ink to a satin or flat finish. Only 5 to 10% of Flattening Paste needs to be added by weight to change the ink's gloss level. Please be aware that the addition of the 3104 Flattening Paste increases the viscosity of the ink.

Use 3 to 5% of 3105 Adhesion Promoter / Catalyst by weight to improve chemical resistance and adhesion. Please note however, that the addition of the 3105 Adhesion Promoter / Catalyst will result in a reduced pot life of 4 to 6 hours under most conditions. We strongly recommend mixing only enough ink for a estimated 4 hour period.

Code	
3901	UV THINNER
3104	FLATTERING PASTE
3105	ADHESION PROMOTER / CATALYST

ADHESION TESTING

It is imperative that all substrates are tested prior to use within production. Even similar materials can very between different batches, manufacturers or the age and storage time of the particular substrate. Certain types of flexible substrates (IE: reinforced vinyl) may be manufactured with plasticizers which can impair ink adhesion and print performance. NXG has been specifically formulated to adhere to most polyethylene substrates with a surface tension levels of 42 to 46 dyne/cm or higher. Conclusive testing regarding the inks final adhesion properties should be completed 24 hours after the initial curing. Once the proper UV energy is achieved, the adhesion should be inspected after the print has cooled down by:

- Observing that the ink is very smooth with a high gloss.
- Cross Hatch Test—Using a sharp blade or cross hatch knife, cut through the film of the ink only, then Apply 3M #600 tape firmly on the cut area.

Rub the tape down firmly then rip off. Ink should only come off in the straight cut areas.

Cure speed and adhesion performance are dependent on the ink opacity, film thickness, color and the overall condition of the curing unit. UV ink under-curing is usually due to excessive ink deposit and/or a poorly maintained UV curing unit.

PRODUCT RANGE

The NXG Ink Series includes the Single Pigment Mixing Colors, Standard Colors and the Advanced Color Gamut™ four-color process inks.

Single pigment mixing colors

Code	
NXG-01	GREEN SHADE YELLOW
NXG-02	RED SHADE YELLOW
NXG-03	YELLOW SHADE RED
NXG-04	BLUE SHADE RED
NXG-05	MAGENTA
NXG-06	MAROON
NXG-07	VIOLET
NXG-08	RED SHADE BLUE
NXG-09	GREEN SHADE BLUE
NXG-10	BLUE SHADE GREEN
NXG-11	YELLOW SHADE GREEN

Standard colors

Code	
NXG-12	LEMON YELLOW
NXG-13	MEDIUM YELLOW
NXG-14	FIRE RED (also a single pigment color)
NXG-15	RUBINE
NXG-16	WARM RED
NXG-17	EMERALD GREEN
NXG-18	PROCESS BLUE
NXG-19	REFLEX BLUE**
NXG-20	ULTRA BLUE**
NXG-21	OPAQUE WHITE





NXG-25	OPAQUE BLACK
NXG-22	TINTING WHITE
NXG-25	OPAQUE BLACK
NXG-27	DENSE BLACK
NXG-30	MIXING CLEAR
NXG-31	OVERPRINT CLEAR
NXG-32	METALLIC CLEAR

^{** 2} year out door light fastness

ADVANCED COLOR GAMUT™ Halftone colors

Code	
NXG-40	HALFTONE YELLOW
NXG-41	HALFTONE MAGENTA
NXG-42	HALFTONE CYAN
NXG-43	HALFTONE BLACK
NXG-44	HALFTONE EXTENDER BASE
NXG-45	HALFTONE HIGH DENSITY YELLOW
NXG-46	HALFTONE HIGH DENSITY MAGENTA
NXG-47	HALFTONE HIGH DENSITY CYAN
NXG-48	HALFTONE HIGH DENSITY BLACK

DURABILITY AND LIGHT-FASTNESS

Although outdoor durability cannot be specified exactly, accelerated weathering tests indicate that the NXG Series Ink Line has an exterior life up to two years on most substrates, with exception to Reflex and Ultra Blue. Reflex and Ultra Blue has an exterior life up to one year. Variables within production and the end products use within the field will greatly affect a printed substrates durability.

A slight change in color and gloss level should be expected.

IMPORTANT NOTE

UV

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.