

# Texsil Auxiliaries

## PRODUCT RANGE

### CATALYSTS

<b>TEXISIL AUSILIARI</b> Code 166650  Package: 1 and 5 kg	Catalyst. Use % = 7 - 10%: 7%: <i>Texsil White 3d, Texsil White Extra, Texsil Matt White, Texsil Opaque Base, Texsil Opaque Matt Base, Texsil Puff Base</i> 10%: <i>Texsil Clear Base, Texsil Matt Transparent</i> Pot life (mixture) = 6 - 8 hours Curing temperature = 130°C during 3 minutes <i>Texsil Catalyst</i> is indicated for printing with automatic machines
<b>TEXISIL CATALYST SUPER FAST</b> Code 166654  Package: 1 and 5 kg	Catalyst. Use % = 3 - 5% Pot life (mixture) = up to 3 hours Curing temperature = 90°C during 2-3 minutes <i>Texsil Catalyst Super Fast</i> is indicated for manual printing

### THINNERS

<b>TEXISIL THINNER</b> Code 166651  Package: 1 Litro	Thinner. It reduces ink viscosity without compromising the opacity; it is useful for the application of silicone inks when working on multi-colour automatic machines. <ul style="list-style-type: none"> <li>• The maximum use percentage is 5%.</li> </ul>
<b>TEXISIL THINNER FAST</b> Code 166652  Package: 1 Litro	Thinner. It reduces ink viscosity without compromising the opacity; it is useful for the application of silicone inks when working on multi-colour automatic machines. It reduces the intermediate drying times with FLASH lamps. <ul style="list-style-type: none"> <li>• The maximum use percentage is 5%.</li> </ul>

## SPECIAL INSTRUCTIONS

- Always test the printing characteristics, before starting production.
- Always check curing conditions. The addition of additives could require different curing temperature and time.

**IMPORTANT NOTE**

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

**WARNING**

This technical data sheet does not replace either the Safety Data Sheet or the specific Conformity Declaration. These documents may be required to our SHEQ (Product safety office), at the following e-mail address: [safety@eptainks.com](mailto:safety@eptainks.com)

The technical data sheet does not relieve the printer, who remains the only responsible of the respect of the regulations, the specifications and the related required certifications of the finished items